


- Features:
- Excellent dimensional stability
 - Excellent lay-flat characteristics
 - Improved slip and anti-static characteristics for sheeting and die cutting
 - High adhesion skin layer provides excellent adhesion with solvent based, conventional offset inks



- Application:
- Transparent BOPP film for in- mold labeling, suitable for sheet-fed and roll-fed printing. It can be used for other kinds of applications such as cut & stack.... as well.

Specification	Test Method	Unit	Test direction	50 μ	57 μ
Wetting Tension	ASTM D 2578	Dyne/cm	N	≥ 36	
			T	≥ 36	
Yield	ASTM D 4321	m ² /Kg	-	22.0	19.3
Gloss	ASTM D 2457	%	-	90	
Haze	ASTM D 1003	%	-	4	
Tensile Strength	ASTM D 882	N/mm ²	MD	140	
			TD	270	
Elongation at break	ASTM D 882	%	MD	200	
			TD	30	
Thermal Shrinkage	ASTM D 1204	%	MD	≤ 4	
			TD	≤ 2	
Dynamic C.O.F	ASTM D 1894	-	N-N	0.35	
			Film-Metal	0.25	

T: Film roll out- side, N: Film roll in- side, MD: Machine direction, TD: Transverse direction

Storage and Handling : The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use. The treatment level declines with time.

Food Approval : Polilux LPB 132 is appropriate to food contact regulation.

Disclaimer : Polilux does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual product shipped. NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polilux denies any responsibility for any loss or damage that may occur from the use of this information. Polilux strongly suggests that before any vast usage, make sure to study "Customer's Guide " and test our product in limited amounts.