


LPB 132

Transparent BOPP Film

Features:

- Excellent dimensional stability
- Excellent lay-flat characteristics
- Improved slip and anti-static characteristics for sheeting and die cutting
- Super clear
- Suitable for offset sheet fed printing with UV curing and oxidative drying inks
- Suitable for gravure and UV-flexo printing (for reel to reel printing with UV inks, inline corona treatment is strongly recommended)
- Suitable for letter press and screen printing

Application: Transparent BOPP film for in- mold labeling, suitable for sheet-fed and roll-fed printing. It can be used for other kinds of applications such as cut & stack.... as well.



Specification	Test Method	Unit	Test direction	50 μ	57 μ
Wetting Tension	ASTM D 2578	Dyne/cm	N	≥ 38	
			Т	≥ 38	
Yield	ASTM D 4321	m²/Kg	-	22.0	19.3
Gloss	ASTM D 2457	%	-	≥ 90	
Haze	ASTM D 1003	%	-	Max 3%	
Tensile Strength	ASTM D 882	N/mm²	MD	140	
			TD	270	
Elongation at break	ASTM D 882	%	MD	200	
			TD	30	
Thermal Shrinkage	ASTM D 1204	%	MD	≤ 4	
			TD	≤ 2	
Dynamic C.O.F	ASTM D 1894	_	N-N	≤ 0.35	
		•	Film-Metal	≤ 0.7	25

T: Film roll out- side, N: Film roll in- side, MD: Machine direction, TD: Transverse direction

Storage and Handling: The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration

of film properties. All films should be allowed to reach operation room temperature for 24 hours before use. The treatment level declines with time.

Food Approval: Polilux LPB 132 is appropriate to food contact regulation.

Polilux does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual Disclaimer:

product shipped.NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polilux denies any responsibility for any loss or damage that may occur from the use of this information. Polilux strongly suggests that before any vast usage, make sure to study "Customer's Guide" and test our product in limited amounts.

Polilux Plastik Film Sanayi ve Ticaret A.Ş.Ulaş OSB Mahallesi, 105. Sok. No:3 Ergene, Tekirdağ, Türkiye Phone : +90 (282) 686 70 00 / Fax : +90 (282) 686 12 12

Date: 01.01.2023