

TBK 121

Transparent BOPP Film

- Good gloss and clarity
- Excellent ink adhesion
- Both sides heat sealable
- Good Stiffness
- Good wire-sealing property in bag-making machines
- Excellent antistatic property to avoid dust accumulation on film surface

OPP Layer-OPP Layer-Sealable layer-Application: ■ General purpose packaging film for using on HFFS and VFFS machines. It can be used as single ply or as lamination substrate to itself and to other films.

Treated sealable layer

OPP Layer

Moreover this film can be used for bag-making to be used in textile packaging.

Specification	Test Method	Unit	Test direction	20 μ	25 μ	27 μ	30 μ	35 μ	40 μ
Wetting Tension	ASTM D 2578	Dyne/cm	Treated Side	≥ 38					
Yield	ASTM D 4321	m²/Kg	-	54.9	43.9	40.7	36.6	31.4	27.4
Haze	ASTM D 1003	%	-	1.5	1.6	1.6	1.7	1.9	2
Gloss	ASTM D 2457	%	-	≥ 96					
Tensile Strength	ASTM D 882	N/mm²	MD	150					
			TD	260					
Elongation at break	ASTM D 882	%	MD	200					
			TD	60					
Thermal Shrinkage	ASTM D 1204	%	MD	≤ 4					
			TD	≤ 2					
Dynamic C.O.F	ASTM D 1894	-	Film-Film	≤ 0.35					
			Film-Metal	≤ 0.30					
Heat Sealing threshold	ASTM F 88	°C	-	≤120					
Heat Seal strength	Internal method	gr cm	-	220					

MD: Machine direction, TD: Transverse direction

Storage and Handling: The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use. The treatment level declines with time.

Food Approval: Polilux TBK 121 is appropriate to food contact regulation.

Polilux does not guarantee the typical values. Any data included herein is based on the analysis of representative samples and not the actual **Disclaimer:**

product shipped.NO guarantee is made regarding information presented in this document. The user is solely responsible for all determinations regarding use and therefore Polilux denies any responsibility for any loss or damage that may occur from the use of this information. Polilux strongly suggests that before any vast usage, make sure to study "Customer's Guide" and test our product in limited amounts.

Polilux Plastik Film Sanayi ve Ticaret A.Ş.Ulaş OSB Mahallesi, 105. Sok. No:3 Ergene, Tekirdağ, Türkiye Phone : +90 (282) 686 70 00 / Fax : +90 (282) 686 12 12

Date: 01.01.2023